

### Technical Datasheet

<b>Company</b>	Vetronova
	0039 0331.311000

<b>Description of the film</b>	FUTURE FOLIEN
	non-food-contact

<b>Type:</b>	P100 A-PET
<b>Colour</b>	clear
<b>Thickness:</b>	700 $\mu$
<b>Tolerance of gauge</b>	+/- 5 %
<b>Reel width</b>	1000 mm
<b>Tolerance of width</b>	+ / - 1 mm
<b>Core diameter</b>	152,4 mm
<b>Reel length</b>	50 lm
<b>Specific weight</b>	1,34 g/cm <sup>3</sup>

<b>A-PET:</b>	amorphous Polyethylenterephthalat
---------------	-----------------------------------

<b>vapour permeability</b>	
<b>oxygen O<sub>2</sub></b>	approx. 1,5 cm <sup>3</sup> / m <sup>2</sup> x d x bar
<b>Nitrogen</b>	not measable
<b>carbonic acid CO<sub>2</sub></b>	approx. 1,3 cm <sup>3</sup> / m <sup>2</sup> x d x bar
<b>steam</b>	approx. 0,12 g / m <sup>3</sup> x d

<b>Thermoforming temperature</b>	95 - 120 °C
<b>Sealing temperature</b>	145 - 170 °C
<b>Vicat-Softening temperature</b>	average temp. 71°C
<b>Shrinkage / toal thickness</b>	longitudinal 3,3% / transverse 3,5 %

<b>storage conditions, recommended</b>	15-25°C, 55-65% rel. Humidity protection against direct UV-Radiation
--	---

10.03.2011